

TECHNICAL INFORMATION

WESTCO DTDM 4,4'dithiodimorpholine

Sulfur donor vulcanizing agent for low sulfur or non-sulfur cure system; provides good heat aging resistance in NR and SR when used with sulfenamide accelerators. Crystal form is free flowing and non-dusting.

Specifications

Appearance	White Crystal
*Initial Melting Point, °C	120 min
*Moisture, %	.5 max
*Ash, %	.3 max
Specific Gravity, typical	1.35
Purity, %	98 min

*Actual data will be reported on Certificate of Analysis

1/08 R