

TECHNICAL INFORMATION

WESTCO ZMBT

(Zinc 2- Mercaptobenzothiazole)

Primary accelerator for NR, SR and their latices; used as a secondary accelerator in sulfur cured latex.

SPECIFICATIONS:

Appearance	Oiled Powder	Unoiled Powder
*Zinc Content, %	15-18	15-18
*Free MBT,%	11-15	11-15
*Moisture,%	0.5 max.	0.5 max.
*Residue on 100 mesh sieve,%	0.3 max.	0.3 max.
*Residue on 230 mesh sieve,%	0.5 max.	0.5 max.
*Oil content, %	1-2	0

TYPICAL PROPERTIES:

Specific Gravity	1.7	1.7
------------------	-----	-----

*Actual data will be reported on Certificate of Analysis

3/09R