

TECHNICAL INFORMATION

WESTCO TIBTD

Name: Tetraisobutylthiuram disulfide

CAS Number : 3064-73-1

Molecular weight :408.756

Product Description

Westco TIBTD is tetraisobutylthiuram disulfide.

Typical Properties

Heat Loss,% (2g, 40°C, 4 hrs)	0.5 Max.
Ash, %	0.5 Max.
Melting Point, °C	65 Min.
Fineness, Residue on 100 Mesh Screen, %	1.0 Max.

General Information

Property	Typical Value
Color	cream to tan
Physical Form	powder

Applications and Uses

- Fast curing primary or secondary accelerator in NR, SBR, NBR rubber and in Chloroprene
- As replacement for TMTD and TETD when nitrosamines are of concern.

The information contained herein has been compiled from sources believed to be reliable and accurate however, all data, use recommendations and statements are made without warranty, expressed or implied, regarding the accuracy, applicability, results from the use of the material, or any hazards associated with the use of the material. It is the responsibility of the user to determine for himself the suitability of the material for his specific uses and further to determine the appropriate safety procedures and precautions necessary for use of the material.

October 2003