

## NOCHEK<sup>®</sup> 4729A Wax

### Technical Data:

**NOCHEK<sup>®</sup> 4729A** is designed to impart ozone resistance to rubber articles used in industrial applications such as tire and rubber, plastics, footwear, etc.

### PHYSICAL PROPERTIES

TEST METHODS	ASTM METHOD	SPECIFICATIONS		TYPICAL
		Minimum	Maximum	
Congealing Point°F (°C)	D 938	151 (66)	156 (69)	154 (68)
Kinematic Viscosity, cSt @ 212°F (100°C)	D 445	5.5	7.5	6.5
Flash Point (C.O.C.), °F, °C	D 92	400(204)	----	-----
ASTM Color	D 6045	----	1.5	0.7
Needle Penetration, dmm @ 77°F (25°C)	D 1321	----	0.1	
Ash Content, Wt%	D 482	----	0.1	----

Note: Physical properties for which ONLY a typical value is listed are included as additional information but may not be printed on the COA.

**FDA STATUS:** This product is not intended for food contact.

Revised 02/2016

The technical information and suggestions for use contained herein are believed to be reliable, but they are not to be construed as warranties and no patent liability can be assumed.