

**WESTCO™ 6PPD Antioxidant-Antiozinant
N-1,3-dimethylbutyl)-N-phenyl-p-phenylenediamine
CAS# 793-24-8**

Technical Data:

WESTCO™ 6PPD is used mainly in the manufacture of tires, rubber shoes and other technical goods. A very effective antioxidant and antiozonant for natural and synthetic rubber. It provides protection against flex cracking and heat aging. Excellent incorporation and easy handling.

Specifications

| | |
|--|-----------------------------|
| Appearance | Violet-Brown Pellets |
| *Melting Point, BFG Capillary Tube Method | 45° C Min. |
| *Purity | 95% Min. |
| *Moisture | 0.5% Max. |
| *Ash | 0.1% Max. |
| Specific Gravity | 1.02 |
| Packaging: 25 kg net weight/bag 500 kg net weight/super sacks | |

***Actual data will be reported on Certificate of Analysis**

Revised 7/2015

The technical information and suggestions for use contained herein are believed to be reliable, but they are not to be construed as warranties and no patent liability can be assumed.