

WESTCO™ BDMC Accelerator
Bismuth dimethyldithiocarbamate
CAS# 21260-46-8

Technical Data:

WESTCO™ BDMC is a secondary accelerator for rubber compounds. It will significantly increase the cure rate when used in conjunction with sulfur based cure systems utilizing thiazole or sulfenamide primary accelerators. It can be used as a lower cost alternative to Tellurium Diethyldithiocarbamate (TDEC), especially in EPDM compounds.

Specifications

Appearance:	Light yellow powder
*Bismuth content	35-42%
*Melt point	230°C Min.
*Moisture	1.0% Max.
*Sieve residue (100 mesh)	0.5% Max
Specific gravity	2.04 typical

Packaging: 20kg Kraft paper bags

**Shelf Life: 24 months from date of manufacture when stored @ 40°C
Maximum; away from direct light and moisture.**

***Actual data will be reported on Certificate of Analysis**

Revised 7/2015

The technical information and suggestions for use contained herein are believed to be reliable,
but they are not to be construed as warranties and no patent liability can be assumed.