

**WESTCO™ DTDC
CAS # 23847-08-7**

WESTCO™ DTDC is a vulcanizing agent for natural rubber and synthetic rubber. It is a non-nitrosamine alternative for DTDM that promotes excellent mechanical properties, heat resistance and low compression sets and is well suited for natural rubber and synthetic rubber. WESTCO DTDC is blended with a 3% maximum of level of silica to prevent product caking or compaction during transit and storage

Appearance

Light to off-white powder

Specifications

*Initial Melting Point	120 °C min
*Moisture	.5 % max
*Ash	3.5% max
*Sieve Residue (100 Mesh)	.3% max
*Oil Content	1.0% max
*Actual data will be reported on Certificate of Analysis	

Reviewed 04/2016

The technical information and suggestions for use contained herein are believed to be reliable, but they are not to be construed as warranties and no patent liability can be assumed.