

## **WESTCO™ DTDC-80 Accelerator**

### **CAS # 23847-08-7**

WESTCO™ DTDC-80 is an 80% active polymer bound dispersion with an EPDM/EVM binder. It is a non-nitrosamine alternative for DTDM that promotes excellent mechanical properties, heat resistance and low compression sets and is well suited for natural rubber and synthetic rubber.

**\*Appearance**

**Off white pellets or granules**

**Specifications**

<b>Initial Melting Point</b>	<b>120 °C min</b>
<b>*Density(g/c m<sup>3</sup>)</b>	<b>1.07-1.17</b>
<b>Mooney ML (1-4)</b>	<b>50</b>
<b>Purity (DTDC)</b>	<b>97% min</b>
<b>*Sulphur Content</b>	<b>16.0-19.0%</b>
<b>Moisture</b>	<b>.5 % max</b>
<b>Ash</b>	<b>.5% max</b>
<b>Sieve Residue (230 Mesh) (DTDC only)</b>	<b>.8% max</b>

\*Actual data will be reported on Certificate of Analysis

Reviewed 04/2016

The technical information and suggestions for use contained herein are believed to be reliable, but they are not to be construed as warranties and no patent liability can be assumed.